PRODUCT'S CARD

SANMED C-463

Usage

Coating - PU	100%
Backing - PES	100%
Weight [g/m2]	180 ± 20 (110 cm) 155 ± 15 (145 cm)
Water tightness [mm water column]	≥ 2000
Vapor permeability	≥ 300
Adhesion [daN/5cm] Method 2 along / across	≥ 20 / ≥ 10
Flame retardancy	+
Flame retardancy	+
Flame retardancy	PN EN 1021-1 PN EN 1021-2

PRODUCT'S CARD

SANMED C-463

REACH

OEKO-TEX

Attestation of the Polish Institute of Hygiene

Phtalates free

Antibacterial

Fireproof

Breathable

Permeable

Waterproof