



PRODUCT'S CARD

SKILTEX L-682

Usage



Coating - PES	26%
Backing - PES	74%
Backing - PP	26%
Adhesion [daN/5cm] Method 2 along / across	≥ 30 / ≥ 20
Tear strength along / across [daN] Method B	≥ 3 / ≥ 3
Adhesion of the coating - along / across [daN/5cm]	≥ 1 / ≥ 1
Resistance to repeated bending at room [number of bends in thousands]	≥ 150
Resistance to repeated bending at set temperature [number of bends in thousands]	$-15^{\circ}\text{C} \geq 10$